

Dynactiv™ 130

Application	UPHOLSTERY
Composition	PVC 90 %, PES 10 %
Width	140 cm
Roll length	30 lm
Weight	650 g/m ² ± 5 %
Thickness	1,2 mm ± 0,2 mm

Property	Method Trial	Unit	Along	Across
Tensile strength	DIN 53354	daN/5 cm	≥ 39,55	≥ 25,88
Tensile elongation	DIN 53354	%	≥ 69	≥ 194
Tear strength	DIN 53356	daN/5 cm	≥ 2,21	≥ 2,92
Sewing test	DIN 53506	daN/5 cm	≥ 28,36	≥ 17,52
Sewing elongation	DIN 53506	%	≥ 64	≥ 171

HOM = Frequency of analysis when accrediting the material and each 75 lots.

PO-LC.805.5

ADDITIONAL INFORMATION



Abrasion resistant:
ISO 5470-2
25.600 cycles (12kPa)



**Color-fast to
artificial light (≥ 6)**



Hygienic material



**Resistant to salty
environment**



Available from stock

In order to maintain the original aspect of this quality, it's strongly recommended to clean regularly. First use a wet sponge with lukewarm water and neutral soap; then rinse it with normal water.

Avoid great amounts of water to insure does not penetrate into the seams.

Before using a special cleaning product it's recommended to test in advance to verify its use doesn't deteriorate the article or contact Benecke-Kaliko for approval.



The content of this publication is not legally binding and is provided as information only. The trademarks displayed in this publication are the property of Continental AG and/or its affiliates. Copyright © 2015 ContiTech AG. All rights reserved. For complete information go to: www.contitech.de/discl_en