

Dynactiv™ 675

Application	INDOOR UPHOLSTERY
Composition	PVC 88 %, POLYESTER 8 %, COTTON 4 %
Width	140 cm
Roll length	30 lm

Property	Method Trial	Unit	Min.	Max.	Fr.
Weight	ISO 2286-2	g/m ²	740	880	1
Thickness	ISO 2286-3	mm	1.00	1.20	1
Tensile Strength L (daN)	ISO 1421	daN/5 cm	30		1
Tensile Strength T (daN)	ISO 1421	daN/5 cm	24		1
Tear Strength Resistance L (daN)	ISO 4674 A2	daN	2.0		1
Tear Strength Resistance T (daN)	ISO 4674 A2	daN	1.8		1
Martindale	ISO 12947	cycles	125000		25
Xenotest	ISO 105-B02	NOTE BS	6.0		HOM

HOM = Frequency of analysis when accrediting the material and each 75 lots.

PO-LC.805.5

ADDITIONAL INFORMATION



Effective against fungus and bacteria



Protective finish



Fire proof norm:
IMO A652, EN 1021 (1-2),
M2, AM18, B2, BS 5852
(Crib5), UNI 9175,
CAL-TB 117, FAR 25853



Resistant to salty environment



The product's formulation is phthalate-free



BV 0062 Wheel Mark



Available from stock

In order to maintain the original aspect of this quality, it's strongly recommended to clean regularly. First use a wet sponge with lukewarm water and neutral soap; then rinse it with normal water. Avoid great amounts of water to insure does not penetrate into the seams. Before using a special cleaning product it's recommended to test in advance to verify its use doesn't deteriorate the article or contact Benecke-Kaliko for approval.



BK 06/16 (EN)

The content of this publication is not legally binding and is provided as information only. The trademarks displayed in this publication are the property of Continental AG and/or its affiliates. Copyright © 2016 ContiTech AG. All rights reserved. For complete information go to: www.contitech.de/discl_en