

Dynactiv™ 160

Application	UPHOLSTERY
Composition	PVC 89 %, COTTON 11%
Width	140 cm ± 2 cm
Roll length	30 lm

Property	Method Trial	Unit	Min.	Max.	Fr.
Weight	ISO 2286-2	g/m ²	740	860	1
Thickness	ISO 2286-3	mm	1.20	1.45	1
Tensile Strength L (daN)	ISO 1421	daN/5 cm	22		1
Tensile Strength T (daN)	ISO 1421	daN/5 cm	13		1
Tear Strength Resistance L (daN)	ISO 4674 A2	daN	1.2		1
Tear Strength Resistance T (daN)	ISO 4674 A2	daN	1.2		1
Martindale	ISO 12947	cycles	150000		25
Xenotest	ISO 105-B02	NOTE BS	6.0		HOM

HOM = Frequency of analysis when accrediting the material and each 75 lots.

PO-LC.805.5

ADDITIONAL INFORMATION



Effective against fungus and bacteria




Fire proof norm:
EN 1021 (1-2), M2, B2,
BS 5852 (CRIB 5), IMO A652



Protective finish



Resistant to salty environment



BV 0062 Wheel Mark



Available from stock

In order to maintain the original aspect of this quality, it's strongly recommended to clean regularly. First use a wet sponge with lukewarm water and neutral soap; then rinse it with normal water.

Avoid great amounts of water to insure does not penetrate into the seams.

Before using a special cleaning product it's recommended to test in advance to verify its use doesn't deteriorate the article or contact Benecke-Kaliko for approval.



The content of this publication is not legally binding and is provided as information only. The trademarks displayed in this publication are the property of Continental AG and/or its affiliates. Copyright © 2016 ContiTech AG. All rights reserved. For complete information go to: www.contitech.de/discl_en